


Product data sheet



Material properties (This data are typical values and are not to be construed as product specifications.)

Test/Composition	Typical Value	Unit	Method
Density	0.949	g/cm ³	ISO1183
Fish Eye Note	≤3	note	Internal
FRR 21.6/5	29		
MFR 190°/21.6	8.0	g/10min	ISO1133
MFR190°/5	0.28	g/10min	ISO1133

- Test specimen from compression moulded sheet at 23°C.

- FRR values are statistical and calculated by dividing MFR values.

- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values